

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 116 755 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
18.07.2001 Bulletin 2001/29

(51) Int Cl.7: **C09D 11/00, B41M 3/14**

(21) Application number: **00810019.0**

(22) Date of filing: **10.01.2000**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

(72) Inventors:
• **Egger, Philipp**
1004 Lausanne (CH)
• **Müller, Edgar**
1006 Lausanne (CH)

(71) Applicant: **SICPA HOLDING S.A.**
1008 Prilly (CH)

(74) Representative: **Hepp, Dieter et al**
Hepp, Wenger & Ryffel AG,
Friedtalweg 5
9500 Wil (CH)

(54) **Coating composition, preferably printing ink for security applications, method for producing a coating composition and use of glass ceramics**

(57) The present invention relates to coating compositions, preferably printing inks for security applications comprising at least one organic resin, at least one pigment and optionally at least one organic solvent. Said pigment comprises glass ceramic composite particles, containing at least one crystalline particle embedded in a glass matrix. Said glass ceramic particles have a particle size in the range of between 0.1 μm to 50 μm . Preferably active ions selected from the group of the rare-

earth elements are incorporated into the crystalline phase of the composite to provide the glass ceramics with luminescent up- and down converting characteristics. Glass ceramic luminescents have excellent physical and chemical stability. The glass matrix permits as well the stabilisation of the photophysically interesting halide host crystals which have low phonon energies. Such materials provide unusual excitation and emission properties.

EP 1 116 755 A1

Description

[0001] The present invention relates to a coating composition, preferably a printing ink for security applications, to a method for producing a coating composition and to the use of glass ceramics according to the preambles of the independent claims.

[0002] Pigments which have luminescent properties (phosphors) are well known and are widely used as marking materials in security applications. Luminescent materials can absorb certain types of energy acting upon them and subsequently emit this absorbed energy as electromagnetic radiation. Down-converting luminescent materials absorb electromagnetic radiation at a higher frequency (shorter wavelength) and re-emit it at a lower frequency (longer wavelength). Up-converting luminescent materials absorb electromagnetic radiation at a lower frequency and re-emit part of it at a higher frequency. Luminescent materials are used for coding and marking of mass-produced goods, high value branded articles and security documents. In certain cases an up-converting luminescent is added as a hidden "taggant" to a transparent or colorless coating composition or printing ink, which is applied to branded goods in form of barcodes, company emblems, labels, etc. This allows a subsequent recognition of the genuine article in the fight against counterfeiters and product piracy.

[0003] Light emission of luminescent materials arises from excited states in atoms or molecules. The radiative decay of such excited states has a characteristic decay time, which depends on the material and can range from 10^{-9} seconds up to various hours.

[0004] Short-lived luminescent emission is usually called fluorescence, whereas long-lived emission is called phosphorescence. Materials of either type of emission are suitable for the realisation of machine-readable codes. Machine-readability is a necessary prerequisite for mass treatment of goods, e.g. in automated production, sorting, quality control, packaging or authentication operations. Machine-verification is also applied outside production or logistic chains for counterfeit or fraud detection.

[0005] The common up-converting materials are of inorganic nature and consist essentially of a crystal lattice in which rare-earth ions are present as activators and sensitizers. The excitation and emission characteristics of up-converting materials are inherent characteristics of the rare earth ions employed. Their corresponding optical absorption and emission processes are due to electron transitions within the incompletely filled 4f shell of the rare earth ion. This electron shell is strongly shielded from the chemical environment of the atom, such that variations in the crystal lattice, thermal vibrations, etc. have only a marginal influence on it. Consequently, rare-earth ions have narrow band optical absorption and emission spectra, which are to a great extent independent of the nature of the crystal lattice. The sharp, discrete bands and the low interaction with the crystal lattice usu-

ally result in a high saturation of the luminescence color and a high luminescence quantum yield.

[0006] Rare-earth ion luminescence activators have relatively long-lived excited states and a particular electronic structure. This permits the energy of two or more photons in succession to be transmitted to one single luminescence centre and cumulated there. An electron is thus promoted to a higher energy level than that corresponding to the incoming photon energy. When this electron returns from its higher level to the ground state, a photon having about the sum of the energies of the cumulated exciting photons is emitted. In this way it is possible to convert e.g. IR radiation into visible light. Alkali and alkaline earth metal halides, and the halides, oxyhalides and oxysulfides of yttrium, lanthanum and gadolinium are principally used as the host material, whereas e.g. Er^{3+} , Ho^{3+} and Tm^{3+} serve as the activators. Additionally, ytterbium(3+) and/or other ions can be present in the crystal lattice as sensitizers to increase the quantum yield.

[0007] Down-converting luminescents are either of inorganic or of organic (molecular) nature. Irradiation of the luminescent with short-wave light promotes an electron to a higher excited state. Decay of this higher excited state usually follows a cascade to next-lower excited states, and finally to the ground state, and produces light emissions having longer wavelength than the exciting radiation. Typical down-converting luminescents convert UV to visible light. Conversion of UV or visible light to IR, or of lower wavelength IR to higher wavelength IR is also possible. Usually up-converting luminescents can also be exploited in down-converting modes.

[0008] However a lot of up-and down-converting materials are not stable when exposed to oxygen, humidity, and, in particular, to organic solvents and/or media containing chemical oxidising or reducing agents. Thus the choice of luminescent materials, particularly of up-converters which are suitable for being blended as pigments into polymer compositions, such as coating composition or printing inks, is limited to only a few types of host crystals.

[0009] GB 2 258 659 and GB 2 258 660 describe up-converting materials based on yttrium oxysulfide ($\text{Y}_2\text{O}_2\text{S}$), doped with erbium and ytterbium. Further disclosed is the use of such materials as pigments in printing inks for security applications.

[0010] Since compositions, synthesis and absorption/emission properties of the common up- and down-converting materials fulfilling the necessary stability criteria are more and more known to counterfeiters as well, there is a constant need for new up-and down-converting materials, having uncommon composition and properties, such as particular luminescence decay characteristics, and/or particular luminescence efficiency and/or, in its case, particular branching ratios between multiple emission possibilities, all of them being exploitable for security purposes.

[0011] It is an object of the present invention to overcome the drawbacks of the prior art.

[0012] Particularly it is an object of the invention to provide new luminescent pigments, especially those having unusual excitation/emission characteristics. It is a further object of the invention to provide up- and down-converting pigments which are resistant to environmental influences, particularly against organic resins and/or solvents.

[0013] These objects are solved by the features of the independent claims. Particularly they are solved by a coating composition, preferably a printing ink for security applications, comprising at least one organic resin, at least one pigment and optionally at least one solvent, characterised in that said pigment comprises glass ceramic particles which contain at least one crystalline phase embedded in a glass matrix, said pigment having a particle size in the range of between 0.1 μm to 50 μm .

[0014] Preferably the glass ceramic particles have a particle size in range of between 1 μm to 20 μm and even more preferably in the range of between 3 μm to 10 μm .

[0015] Glass ceramics are composite solids, which are formed by controlled devitrification of glasses. (See Römpp Chemie Lexikon, ed. J. Felbe, M. Regitz, 9th edition 1990, page 156.) They can be manufactured by heating (tempering) suitable precursor glasses to allow for partial crystallisation of part of the glass composition. Glass ceramics comprise thus a certain amount of a crystalline phase, embedded in a surrounding glass phase.

[0016] In a preferred embodiment of the present invention the crystalline phase of the glass ceramics comprise a luminescent material. This is of particular interest and value for luminescent materials, which are not stable in an ordinary environment, and which can in this way be protected from the adverse influence of oxygen, humidity, etc. The glass matrix protects the crystalline phase from dissolution in an adverse environment, and permits incorporation into a coating composition or the like. New types of luminescent materials are thus amenable to printing applications by this method.

[0017] Many photophysically interesting luminescent host materials are e.g. water soluble to a certain extent, like the fluorides, chlorides or bromides of the lanthanide elements. The solubility is due to the rather weak electrostatic crystal lattice forces tied to mono-negative anions. The same materials show, due to the same reason and/or to the presence of heavy ions, only low-frequency vibrational modes (phonon modes) of their crystal lattices. The absence of high-frequency vibrational modes results in largely increased excited state life times and luminescence quantum yields. The reason for this is that the probability of vibrational desexcitation of an electronically excited activator ion is low if the energy gap to the next lower lying electronic level is much larger than the energy of the highest vibrational mode (phonon energy) of the crystal lattice. Energy transfer to the crys-

tal lattice becomes negligible in such cases. Host materials with low phonon energy would thus be highly desirable, especially in the field of up-converting phosphors where long-lived excited states are needed for achieving high quantum yields. The water-solubility and moisture sensitivity of lanthanide halides and related materials has up to now prevented corresponding technical applications.

[0018] Preferably the crystalline component of the glass ceramics has a phonon energy not exceeding 580 cm^{-1} , preferably not exceeding 400 cm^{-1} and even more preferably not exceeding 350 cm^{-1} . These values stand for rather low-phonon energy, which are especially suitable as luminescence hosts because they allow for emissions from excited energy levels that would otherwise be quenched in high phonon energy solids, such as oxides or the like.

[0019] Phonons, as mentioned, are crystal lattice vibrations in a material. The relevant phonon energy is tied by Planck's relationship $E=h\nu$ to the frequency ν of the highest measured MIR absorption band of the compound. If an excited rare earth ion has a transition possibility between two energy levels of interest, that corresponds to only a few times the phonon energy of the host lattice, the energy will be preferably and rapidly dissipated to the crystal lattice, without emission of electromagnetic radiation (radiationless transition). In a host lattice with much lower phonon energy, the same transition will preferably radiate. In intermediate cases, both processes, radiating, and radiationless desactivation, will compete with each other.

[0020] In the Pr^{3+} ion, the $^1\text{G}_4$ level of Pr^{3+} is only 3000 cm^{-1} above the $^3\text{F}_4$ level. In an oxide matrix, such as a praseodymium glass, only few Si-O vibration phonons (1100 cm^{-1}) are required to bridge this gap. Thus any excited electron in the $^1\text{G}_4$ level will rapidly return to the $^3\text{F}_4$ level by exciting crystal lattice phonons, and no electromagnetic radiation of the corresponding wavelength is produced. In a Pr^{3+} doped LaF_3 matrix, the phonon energy is 350 cm^{-1} , and the $^1\text{G}_4$ to $^3\text{F}_4$ transition of the Pr^{3+} ion occurs radiatively. Additionally, the live time of the $^1\text{G}_4$ state is strongly increased.

[0021] Since phonon energies are controlled by the bond strengths and the masses of the ions forming the crystal lattice, heavy elements with weak bonding will provide the lowest phonon energy materials. The heavy metal fluoride glasses such as e.g. ZBLAN ($53\text{ZrF}_4 \cdot 20\text{BaF}_2 \cdot 4\text{LaF}_3 \cdot 3\text{AlF}_3 \cdot 20\text{NaF}$) have half the maximum phonon energy of silicates and thus take twice as many phonons to quench the $^1\text{G}_4$ level of Pr^{3+} . ZBLAN glasses, a well known host lattice for laser and fibre-optic applications, can also be used as the glass component of glass ceramic composites according to the present invention.

[0022] Preferably the glass ceramic is substantially transparent to electromagnetic radiation in the range of between 400 nm to 750 nm, i.e. in the visible range of the electromagnetic spectrum. Transparency of glass

ceramics are determined by the average dimensions of the embedded crystals and/or the refractive index difference between the crystals and the glass matrix.

[0023] In a preferred embodiment average dimensions of the crystals are not exceeding 50 nm, preferably not exceeding 40 nm. Exceeding crystal size results in opaqueness of the glass ceramic.

[0024] Preferably, the average distance from one embedded crystal to another in the glass matrix should be in the order of the crystal size, e.g. not exceeding 50 nm and preferably not exceeding 40 nm. Apart from transparency another important aspect is the protection of the crystals by the glass matrix. Those host crystals having poor stability towards environmental influences and being neither physically nor chemically resistant towards organic resins, solvents, humidity, etc. can efficiently be protected by a glass matrix having such chemical and physical resistance. If the size of the embedded crystals are according to the preferred embodiment of the present invention, the grinding of the glass ceramics to pigment size particles is surprisingly possible without adversely affecting the luminescent properties of the glass ceramics. The photoactive crystals remain thus protected by the surrounding glass matrix.

[0025] In a preferred embodiment at least one crystal in the glass matrix comprises an active ion.

[0026] In the context of the present invention the active ion being present in at least one of the crystals in the glass matrix are rare earth ions having an appropriate electronic structure, particularly suitable are rare earth ions selected from the group consisting of Pr^{3+} , Nd^{3+} , Sm^{3+} , Eu^{3+} , Tb^{3+} , Dy^{3+} , Ho^{3+} , Er^{3+} , Tm^{3+} and Yb^{3+} .

[0027] In a preferred embodiment of the present invention the glass ceramics is an oxyfluoride glass ceramics. Oxyfluorides have the low phonon energy of a fluoride matrix and the durability and mechanical properties of an oxide glass. The oxide glass will determine the mechanical and physical properties of the composite whereas the optical properties of the active ion will be controlled by the embedded fluoride crystalline phase.

[0028] A preferred glass matrix in the present invention for oxyfluorides consists essentially of NAS glass ($\text{Na}_2\text{O} \cdot \text{Al}_2\text{O}_3 \cdot \text{SiO}_2$). NAS as host glass shows favourable properties with respect to melting and forming, good transparency and excellent durability. The content of SiO_2 preferably is between 30 mol% to 90 mol% of the mols of the glass, preferably between 50 mol% and 80 mol%. The higher the SiO_2 content in the glasses the more viscous they get and the easier they can be formed into large blocks. However, the fluoride retention is less than in glasses which have a SiO_2 content towards the lower limit. The SiO_2 can be replaced e.g. by GeO_2 and Al_2O_3 by Ga_2O_3 . The alkali content (Na_2O) can be replaced fully or partly by other alkalis, mixture of alkalis or alkaline-earths such as BaO . Many other ingredients can be added to the NAS glass in order to modify and tailor the refractive index, expansion, durability, density

and color of the glass matrix.

[0029] Preferably the crystal phase in the oxyfluorides comprise LaF_3 . LaF_3 -glass ceramics can be manufactured by heat treating (tempering) Al_2O_3 rich NAS glass saturated with LaF_3 . The solubility of LaF_3 is determined by the Al_2O_3 in the glass. LaF_3 levels far below the solubility limit results in stable glasses that do not form glass ceramics when heat treated. Therefore the content of LaF_3 in the glass has to be within $\pm 15\%$, preferably 10 % of the solubility limit of LaF_3 . In case the alkali content is replaced by alkaline-earth compositions the solubility of LaF_3 is raised. Therefore the amount of LaF_3 should be increased. LaF_3 glass ceramics shows a chemical resistance which is in many aspects better than glass ceramics used before, e.g. ZBLAN glass ceramics.

[0030] The LaF_3 crystal phase allows the partition of any rare earth. Therefore a huge variety of up- and down converting materials with very unusual electronic structures can be provided, which are responsive to excitation radiation not commonly used in product security. Thus those glass ceramics in combination with at least a two photon excitation according to the advanced product security system of the present invention broadens the application of up-converters substantially.

In a preferred embodiment the oxyfluoride glass ceramics is transparent and colorless to the human eye.

[0031] By controlling the correct microstructure, transparency of oxyfluoride glass ceramics may be achieved which is equivalent to best optical glasses. Generally the microstructure of the LaF_3 glass ceramics is a function of the heat treatment temperature. When heat treated at 750°C for 4 h a large number of relatively small (ca. 7 nm) LaF_3 crystals are visible. At higher temperature the crystallites grow larger. At 800°C the average crystal has a dimension of 20 nm and at 825°C over 30 nm average crystallite size is observed. Since appropriate crystallite size is the main influence factor for transparency, the glass ceramics formed at 750°C for 4 h resulted in the most transparent of all. Even with the increase of crystallite size related with the heat treatment up to 775°C the transparency was still higher than of untreated material. The transparency is measured as a function of the extinction which is the sum of the total loss of scattering and absorption effects. Above 850°C the oxyfluoride glass ceramics becomes opaque.

[0032] The tempered glass ceramic can be ground to pigment. Optimal particle size for most printing applications is in the order of 3 to 10 μm . After incorporating such transparent oxyfluoride glass ceramic particles into a transparent coating or ink vehicle, an invisible product coding can be applied to a substrate. Since the oxyfluoride glass ceramic pigments can be designed with emission properties which do not respond to the excitation radiation of commonly used wavelengths it becomes very difficult for a potential counterfeiter to localise and identify the marking or to retro-engineer the pigment.

[0033] The coating composition, preferably printing ink, of the present invention further comprises binders. The binders used in the present invention may be selected from any of the polymers known in the art. Polymers useful in coating composition, preferably printing inks include alkyds, polyurethanes, acrylics, polyvinylalcohols, epoxy-resins, polycarbonates, polyesters, etc. The polymers may be thermoplastic, oxidatively crosslinkable or radiation curable e.g. under UV-radiation. In the latter cases the resins comprise suitable cross-linkable functional groups. Such groups can be hydroxy, isocyanate, amine, epoxy, unsaturated C-C bonds, etc. These groups may be masked or blocked in such a way so that they are unblocked and available for the cross-linking reaction under the desired curing conditions, generally elevated temperatures.

[0034] The above-described polymers can be self-crosslinkable or the coating composition can include a separate cross-linking agent that is reactive with the functional groups of the polymer.

[0035] The coating composition, preferably printing ink, of the present invention can be solvent- or water-borne. Although the printing ink or coating composition of the present invention may be utilized in the form of substantially solid powder or dispersion a rather liquid state is preferred. The organic solvents can be of the polar or apolar type depending on the binder polymers employed.

[0036] Other pigments and or fillers may be present. The term "filler" is defined according to DIN 55943: 1993-11 and DIN EN 971-1:1996-09. Filler is a substance in granular or pulvery form which is insoluble in the other components of the coating composition, preferably printing ink and is used to provide and influence certain physical properties of the overall composition.

[0037] The term "pigment" is to be understood according to the definition given by DIN 55943:1993-11 and DIN EN 971-1:1996-09. Pigments are colouring materials in pulvery or plate-like dimensions which are - contrary to dyes - not soluble in the surrounding medium. Functional pigments such as magnetic, corrosion inhibiting- and/or electroconductive pigments may be employed as well.

[0038] The coating composition, preferably printing ink may comprise other additives, such as rheology control agents, waxes, passive resins, i.e. resins which do not contribute to the film forming process, surfactants, soluble dyes, synergists, photoinitiators, etc.

[0039] The coating composition, preferably printing ink, may be applied to the underlying substrate by any of the known deposition processes, such as spraying, brushing, dipping. Preferably it is applied by printing techniques such as flexo-, gravure-, screen, intaglio, letter press and offset printing.

Claims

1. Coating composition, preferably printing ink for security applications, comprising at least one organic resin, at least one pigment and optionally at least one organic solvent, characterized in that said pigment comprises glass ceramic composite particles which contain at least one crystalline phase embedded in glass matrix, said pigment having a particle size substantially comprised in the range of between 0.1 μm to 50 μm .

2. Coating composition according to claim 1 characterized in that the pigments have a particle size in the range of between 1 μm to 20 μm , more preferably in a range of 3 μm to 10 μm

3. Coating composition according to claim 1 or 2 characterized in that the crystalline phase of the glass ceramic particle comprises a luminescent material.

3. Coating composition according to one of the claims 1 to 3 characterized in that the crystalline phase of said glass ceramic particle has a phonon energy not exceeding 580 cm^{-1} , preferably not exceeding 400 cm^{-1} and even more preferably not exceeding 350 cm^{-1} .

5. Coating composition according to one of the claims 1 to 4 characterized in that the glass ceramic particle is transparent to electromagnetic radiation in the range of between 400 to 750 nm.

6. Coating composition according to one of the claims 1 to 5 characterized in that the crystalline phase of said glass ceramic particle has average dimensions not exceeding 50 nm, preferably not exceeding 40 nm.

7. Coating composition according to one of the claims 1 to 6 characterised in that said crystalline phase of said glass ceramic particle contain at least one active ion for providing long wave to short wave light converting properties.

8. Coating composition according to one of the claims 1 to 7 characterised in that said crystalline phase of said glass ceramic composite contain at least one active ion for providing short wave to long wave light converting properties.

9. Coating composition according to claim 7 to 8 characterised in that said active ion is a rare-earth ion, preferably selected from the group of consisting of Pr^{3+} , Nd^{3+} , Sm^{3+} , Eu^{3+} , Tb^{3+} , Dy^{3+} , Ho^{3+} , Er^{3+} , Tm^{3+} and Yb^{3+} .

10. Coating composition according to one of the claims 1 to 9 characterized in that the glass ceramic particle is an oxyfluoride glass ceramics.

11. Coating composition according to 10 characterized in that the crystalline component of the glass ceramic particle comprises LaF_3 . 5

12. Coating composition according to one of the claims 10 or 11 characterized in that the glass matrix consisting essentially of $\text{Na}_2\text{O} \cdot \text{Al}_2\text{O}_3 \cdot \text{SiO}_2$. 10

13. Security document characterized in that it comprises at least one layer produced by the coating composition, preferably a printing ink, according to one of the claims 1 to 12. 15

14. Use of at least one glass ceramic particle material having luminescent properties as a pigment. 20

15. Method of producing a coating composition, preferably printing ink, comprising glass ceramic particles as pigments comprising the steps of

- providing glass ceramic pigment by comminuting said glass ceramic composite material to the required particle size, 25
- incorporating said glass ceramic pigment into a coating composition or ink formulation, comprising at least one organic resin, at least one pigment and optionally at least one organic solvent. 30

35

40

45

50

55



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 81 0019

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	GB 2 258 659 A (DE LA RUE THOMAS & CO LTD) 17 February 1993 (1993-02-17) The whole document ---	1-15	C09D11/00 B41M3/14
A	GB 2 207 440 A (ERA PATENTS LTD) 1 February 1989 (1989-02-01) * page 3, line 4-12; claim 14 * ---	1	
A	WO 96 03466 A (COOKSON MATTHEY CERAMICS PLC ;CLIFFORD JOHN FRANCIS (GB); WATTS JE) 8 February 1996 (1996-02-08) * claim 1; examples 1,3,4 * -----	1	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C09D B41M
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 16 June 2000	Examiner Von Kuzenko, M
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EP0 FORM 1501 (2.92) (P04/C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 81 0019

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

16-06-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB 2258659 A	17-02-1993	NONE	
GB 2207440 A	01-02-1989	WO 8901226 A JP 2504443 T	09-02-1989 13-12-1990
WO 9603466 A	08-02-1996	AU 3084395 A	22-02-1996

EPO FORM P0159

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82